


40/150 mm

Résultats de production

du 27/07/16 au 22/11/18

	0.063	0.5	20	31.5	40	45	50	63	80	90	100	125	150	200
Maximum	0.56	0.68	0.81	1.22	9.09	15.93	22.43	60.87	72.31	80.25	87.60	93.99	100.00	100.00
Xf+1.25xEcart-types	0.37	0.49	0.63	1.08	8.33	15.75	22.81	55.43	70.79	76.90	85.57	94.16	100.00	100.00
Moyenne Xf	0.19	0.27	0.37	0.61	4.60	10.35	16.69	47.68	65.23	72.28	81.21	91.04	97.86	100.00
Xf-1.25xEcart-types	0.00	0.04	0.11	0.13	0.88	4.94	10.57	39.93	59.67	67.67	76.86	87.92	94.91	100.00
Minimum	0.06	0.10	0.16	0.16	0.48	2.38	7.94	37.53	60.09	67.32	76.33	86.52	93.04	100.00
Ecart-type	0.147	0.179	0.209	0.382	2.980	4.324	4.896	6.200	4.448	3.692	3.481	2.496	2.367	0.000
Nombre de résultats	19	19	19	19	19	19	19	19	19	19	19	19	19	19



WIL 11.04.30.61-2 (c) Arcade

le Responsable Laboratoire

E. COLIN